

QUALITY ASSURANCEKONISHI CO. LTD
SHIGA FACTORY

Minakuchi Industrial Park

1-12, Sasagaoka

Minakuchi-cho, Kokashi

Siga 528-0061, JAPAN

Tel: 0748-62-4340

PRODUCT NAME ; BOND WG200BLUE

1. COMPONENT

COMPONENT	CR Latex, Acrylic Emulsion
-----------	----------------------------

2. GENERAL PROPERTIES

TEST ITEM	TEST METHOD	CONDITION	UNIT	STANDARD
APPEARANCE	JIS K6804	—	—	BLUE LIQUID
VISCOSITY	JIS K6833	BM type viscometer 23°C, rotor No.1, 12r/min	mPa·s	50.0 ~ 200
SOLID CONTENTS	JIS K6828	120°C, 20min	%	55.0 ~ 60.0
pH	JIS K6833	pH meter	—	8.4 ~ 9.0

Guarantee period: Guarantee period is 6 months after manufacturing